



DATASHEET QUATRO GLOSS

quatro

| PARAMETER | STANDARD | UNIT | | | | | | | | | | | | | TOLERANCES |
|----------------------------------|-----------|--------------------|------|------|------|------|------|------|--|--|--|--|--|--|------------------|
| 1 STANDARD QUALITY VALUES | | | | | | | | | | | | | | | ± 2 SIGMA |
| BASIS WEIGHT | ISO 536 | g/m ² | 115 | 130 | 150 | 170 | 200 | 250 | | | | | | | ± 4 % |
| BRIGHTNESS (illuminant D65/10°) | ISO 2470 | % | 95 | 95 | 95 | 95 | 95 | 95 | | | | | | | ± 2 |
| GLOSS DIN 75° (MD) | DIN 54502 | % | 52 | 52 | 52 | 52 | 52 | 52 | | | | | | | ± 5 |
| OPACITY | ISO 2471 | % | 93,5 | 94,5 | 96 | 97 | 98 | 98,5 | | | | | | | ± 2 |
| RELATIVE HUMIDITY (23°C) | TAPPI 502 | % | 50 | 50 | 50 | 50 | 50 | 50 | | | | | | | ± 5 |
| PH VALUE | ISO 6588 | - | >7 | >7 | >7 | >7 | >7 | >7 | | | | | | | - |
| SPEC. VOLUME | ISO 534 | cm ³ /g | 0,73 | 0,73 | 0,73 | 0,75 | 0,75 | 0,72 | | | | | | | ± 6 % |

VALID FROM: 10.01.2008
SUBSTITUTES: 2
REVISION NO: 3
ISSUED BY TECHNICAL & DEVELOPMENT MANAGER: H.Haan