


SORA medico

SORA medico is a woodfree
lightweight uncoated paper.



medico

TS – 30. 4. 2021

	STANDARD	37	40	45	50	60	Tolerance
GRAMMAGE [g/m ²]	ISO 536	37	40	45	50	60	± 2
THICKNESS [μm]	ISO 534	46	49	55	61	72	± 4
SMOOT. BENDTSEN [ml/min]	ISO 8791-2	160	160	160	160	160	max
RELATIVE HUMIDITY [%]	DIN 53118	47.5	47.5	47.5	47.5	47.5	± 7.5
CIE WHITENESS [%]	ISO 11475 (D65/10°)	140	140	140	140	140	± 3
OPACITY [%]	ISO 2471	71	75	78	81	85	min

Given values can be used as guide values only and can be changed without prior notice.
For a valid specification, please refer to the one most recently published on the website www.goricane.si.
Information on the supplies of FSC® and PEFC™ certified products are available in the Sales department.



ISEGA